

Elastohorse Rubber Technology Co.,
#102, Green Field, Pakhowal Road,
Ludhiana ,(Punjab) India.

TECHNICAL DATA SHEET

EASTOMAX 13TH GENERATION RECLAIMING AGENT / RUBBER ACTIVATOR

➤ SPECIFICATION

ITEM	INDEX
Appearance	: Yellow Brown Sticky Liquid
Total Sulphur %	: 13%-14%
Sulphur (Compound)%	: 12% Min
Sulphur (Dissociation)%	: 2% Max
Kinematic Viscosity(60 ⁰)CPS	: 800-6000

➤ APPLICATION

Use of de-vulcanized old tire rubber crumb.

➤ TYPICAL CHARACTERSTICS

Elastomax 13th Generation Reclaiming Agent is a very effective regenerative for natural and synthetic rubber waste and its blends.

➤ STORAGE

To be stored in cool and ventilated warehouse, avoid direct exposure to sunlight.

➤ PACKING

Packing in 1 Kg bottle / 200 kg barrel
